





GP cement is suitable for a wide array of application from household repair to professional applications in Mortars, Concrete, Renders, Grouting & Repair in construction projects. GP cement is grey in Colour. Surelevel GP cement complies with the standards of AS 3972 and EN-197-1 as 52.5 N cement.



## **Physical Properties:**

Property		Standard AS3972
Compressive strength 7 Day	>35 MPa	35 MPa Min
Compressive strength 28 Day	>52.5 MPa	45 MPa Min
Initial Setting Time	>1Hour	45 Minutes Min
Final Setting Time	2.5-5 Hours	6 Hours Max
Soundness	Less than 4mm	5mm Max

## **Health & Safety:**

This product is classified as hazardous according to criteria of Work Safe Australia. Material containing Portland Cement and sand now fall into this category. Continuous or extended contact with this product may cause irritation as well as respiratory issues such as bronchitis or silicosis.

- Ouring use avoid inhalation of dust, contact with skin and eyes.
- Suitable protective clothing, dust masks, gloves and eye protection should be worn.
- Continual or extended contact with cement products can cause skin irritation.
- If skin irritation occurs, remove contaminated clothing and flush skin thoroughly with water for a minimum of 15 minutes. Contact Poisons Information Centre or consult medical adviser.







Safety Data Sheets (SDS) are available on request from the office. Read the SDS and product data sheet carefully before using any product.

Document Date: February, 2024 (REV 4.5)

## **Contact Details**

Entity name: SURE LEVEL INTERNATIONAL PTY LTD Location: 12 Northgate Dr, Thomastown VIC 3074

Phone: + 61 3 9464 5189

Email: info@surelevel.com.au website: www.surelevel.com.au



